

# DuPont™ Crastin® SK692FR NC010

## THERMOPLASTIC POLYESTER RESIN

### Product Information

Common features of Crastin® thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste. If recycling is not possible, DuPont recommends, as the preferred option, incineration with energy recovery (24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

**Crastin® SK692FR is a 15% glass reinforced, flame retardant polybutylene terephthalate for injection moulding.**

General information	Value	Unit	Test Standard
Resin Identification	PBT-GF15FR(17)	-	ISO 1043
Part Marking Code	PBT-GF15FR(17)	-	ISO 11469
Rheological properties	Value	Unit	Test Standard
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0	%	ISO 294-4, 2577
Mechanical properties	Value	Unit	Test Standard
Tensile Modulus	7000	MPa	ISO 527-1/-2
Stress at break	115	MPa	ISO 527-1/-2
Strain at break	2.7	%	ISO 527-1/-2
Charpy impact strength, 73°F	38	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 73°F	6.8	kJ/m <sup>2</sup>	ISO 179/1eA
Thermal properties	Value	Unit	Test Standard
Melting temperature, 18°F/min	223	°C	ISO 11357-1/-3
Temp. of deflection under load, 260 psi	199	°C	ISO 75-1/-2
RTI, electrical			UL 746B
30mil	130	°C	
60mil	130	°C	
120mil	130	°C	
RTI, impact			UL 746B
30mil	130	°C	
60mil	130	°C	
120mil	130	°C	
RTI, strength			UL 746B
30mil	130	°C	
60mil	130	°C	
120mil	130	°C	
Flammability	Value	Unit	Test Standard
Burning Behav. at 60mil nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
UL recognition	yes	-	UL 94
Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
UL recognition	yes	-	UL 94
Glow Wire Flammability Index, 120mil	960	°C	IEC 60695-2-1/2
Glow Wire Ignition Temperature, 120mil	725	°C	IEC 60695-2-1/3
FMVSS Class	DNI	-	ISO 3795 (FMVSS 302)

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

**North America**

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

**Asia Pacific**

Tel: +81 3 5521 8600

**Europe/Middle East/Africa**

Tel: +41 22 717 51 11



# DuPont™ Crastin® SK692FR NC010

## THERMOPLASTIC POLYESTER RESIN

Electrical properties	Value	Unit	Test Standard
Volume resistivity	>1E13	Ohm*m	IEC 60093
Surface resistivity	>1E15	Ohm	IEC 60093
Electric strength	35	kV/mm	IEC 60243-1
Comparative tracking index			
Comparative tracking index	175	-	IEC 60112
0.75mm	3	PLC	UL 746A
Other properties	Value	Unit	Test Standard
Density	1550	kg/m <sup>3</sup>	ISO 1183
Density of melt	1310	kg/m <sup>3</sup>	-
Injection	Value	Unit	Test Standard
Drying Recommended	yes	-	-
Drying Temperature	120	°C	-
Drying Time, Dehumidified Dryer	2 - 4	h	-
Processing Moisture Content	≤0.04	%	-
Melt Temperature Optimum	250	°C	-
Min. melt temperature	240	°C	-
Max. melt temperature	260	°C	-
Mold Temperature Optimum	80	°C	-
Min. mold temperature	30	°C	-
Max. mold temperature	130	°C	-
Hold pressure range	≥60	MPa	-
Hold pressure time	3	s/mm	-
Back pressure	As low as possible		-
Ejection temperature	170	°C	-
Characteristics			
Processing		• Injection Molding	
Delivery form		• Pellets	

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

### Asia Pacific

Tel: +81 3 5521 8600

### Europe/Middle East/Africa

Tel: +41 22 717 51 11




# DuPont™ Crastin® SK692FR NC010


## THERMOPLASTIC POLYESTER RESIN

### Diagrams

#### Viscosity-shear rate




#### Shearstress-shear rate



# DuPont™ Crastin® SK692FR NC010

## THERMOPLASTIC POLYESTER RESIN

Specific volume-temperature (pvT)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

### Asia Pacific

Tel: +81 3 5521 8600

### Europe/Middle East/Africa

Tel: +41 22 717 51 11



# DuPont™ Crastin® SK692FR NC010

## THERMOPLASTIC POLYESTER RESIN

### Chemical Media Resistance

#### Acids

- ✓ Acetic Acid (5% by mass) (23 °C)
- ✓ Citric Acid solution (10% by mass) (23 °C)
- ✓ Lactic Acid (10% by mass) (23 °C)
- ✗ Hydrochloric Acid (36% by mass) (23 °C)
- ✗ Nitric Acid (40% by mass) (23 °C)
- ✗ Sulfuric Acid (38% by mass) (23 °C)
- ✗ Sulfuric Acid (5% by mass) (23 °C)
- ✗ Chromic Acid solution (40% by mass) (23 °C)

#### Bases

- ✗ Sodium Hydroxide solution (35% by mass) (23 °C)
- ✓ Sodium Hydroxide solution (1% by mass) (23 °C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23 °C)

#### Alcohols

- ✓ Isopropyl alcohol (23 °C)
- ✓ Methanol (23 °C)
- ✓ Ethanol (23 °C)

#### Hydrocarbons

- ✓ n-Hexane (23 °C)
- ✓ Toluene (23 °C)
- ✓ iso-Octane (23 °C)

#### Ketones

- ✓ Acetone (23 °C)

#### Ethers

- ✓ Diethyl ether (23 °C)

#### Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23 °C)
- ✗ SAE 10W40 multigrade motor oil (130 °C)
- ✗ SAE 80/90 hypoid-gear oil (130 °C)
- ✓ Insulating Oil (23 °C)

#### Standard Fuels

- ✗ ISO 1817 Liquid 1 - E5 (60 °C)
- ✗ ISO 1817 Liquid 2 - M15E4 (60 °C)
- ✗ ISO 1817 Liquid 3 - M3E7 (60 °C)
- ✗ ISO 1817 Liquid 4 - M15 (60 °C)
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23 °C)
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23 °C)



# DuPont™ Crastin® SK692FR NC010

## THERMOPLASTIC POLYESTER RESIN

- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
- ✗ Diesel fuel (pref. ISO 1817 Liquid F) (>90°C)

### Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✓ Sodium Hypochlorite solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)
- ✓ Zinc Chloride solution (50% by mass) (23°C)

### Other

- ✓ Ethyl Acetate (23°C)
- ✗ Hydrogen peroxide (23°C)
- ✗ DOT No. 4 Brake fluid (130°C)
- ✗ Ethylene Glycol (50% by mass) in water (108°C)
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
- ✓ 50% Oleic acid + 50% Olive Oil (23°C)
- ✓ Water (23°C)
- ✗ Water (90°C)
- ✓ Phenol solution (5% by mass) (23°C)

### Symbols used:

- ✓ possibly resistant

Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

- ✗ not recommended - see explanation

Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 160 mil (Hytrel® measured at 80 mil), IEC Electrical properties measured at 80 mil, all ASTM properties measured at 120 mil, and test temperatures are 73°F unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

Revised: 2017-02-02

Page: 6 of 6

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

#### Asia Pacific

Tel: +81 3 5521 8600

#### Europe/Middle East/Africa

Tel: +41 22 717 51 11



Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.