

# DuPont™ Zytel® 77G43L NC010

## NYLON RESIN

### Product Information

DuPont™ Zytel® LCPA long chain polyamide resins provide an innovative and growing portfolio of flexible polymers with excellent thermal, chemical, and hydrolysis resistance. The diverse selection of Zytel® LCPA grades is targeted for a range of performance characteristics, balancing temperature resistance, flexibility and low permeation.

**Zytel® 77G43L NC010 is a 43% glass fiber reinforced polyamide 612 resin for injection molding.**

General information	Value	Unit	Test Standard
Resin Identification	PA612-GF43	-	ISO 1043
Part Marking Code	PA612-GF43	-	ISO 11469
Rheological properties	dry / cond	Unit	Test Standard
Viscosity number	145 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628
Molding shrinkage, parallel	0.3 / -	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8 / -	%	ISO 294-4, 2577
Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	12500 / 11500	MPa	ISO 527-1/-2
Stress at break	200 / 165	MPa	ISO 527-1/-2
Strain at break	3 / 5	%	ISO 527-1/-2
Flexural Modulus	11000 / -	MPa	ISO 178
Charpy impact strength			ISO 179/1eU
73 °F	100 / 100	kJ/m <sup>2</sup>	
-22 °F	85 / 80	kJ/m <sup>2</sup>	
Charpy notched impact strength			ISO 179/1eA
73 °F	17 / 14	kJ/m <sup>2</sup>	
-22 °F	17 / 13	kJ/m <sup>2</sup>	
-40 °F	17 / -	kJ/m <sup>2</sup>	
Izod notched impact strength			ISO 180/1A
73 °F	17 / -	kJ/m <sup>2</sup>	
-40 °F	15 / -	kJ/m <sup>2</sup>	
Hardness, Rockwell, R-scale	118 / -	-	ISO 2039-2
Thermal properties	dry / cond	Unit	Test Standard
Melting temperature, 18 °F/min	218 / *	°C	ISO 11357-1/-3
Glass transition temperature, 18 °F/min	65 / 55	°C	ISO 11357-1/-2
Temp. of deflection under load			ISO 75-1/-2
260 psi	203 / *	°C	
65 psi	217 / *	°C	
Coeff. of linear therm. expansion, parallel	14 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion			ISO 11359-1/-2
normal	110 / *	E-6/K	
Normal, -40-23 °C	75 / *	E-6/K	
Normal, 55-160 °C	140 / *	E-6/K	
Parallel, -40-23 °C	21 / *	E-6/K	
Parallel, 55-160 °C	13 / *	E-6/K	
RTI, electrical			UL 746B
30mil	105 / *	°C	
60mil	120 / *	°C	
RTI, strength, 60mil	120 / *	°C	UL 746B
Flammability	dry / cond	Unit	Test Standard
Burning Behav. at 60mil nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	yes / *	-	UL 94
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.71 / *	mm	IEC 60695-11-10

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11



# DuPont™ Zytel® 77G43L NC010

## NYLON RESIN

UL recognition	yes / *	-	UL 94
FMVSS Class	B	-	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	21	mm/min	ISO 3795 (FMVSS 302)
<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Relative permittivity, 1MHz	3.6 / -	-	IEC 60250
Dissipation factor, 1MHz	200 / -	E-4	IEC 60250
Volume resistivity	1E13 / -	Ohm*m	IEC 60093
<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Humidity absorption, 80mil	0.7 / *	%	Sim. to ISO 62
Water absorption, 80mil	1.7 / *	%	Sim. to ISO 62
Density	1420 / -	kg/m <sup>3</sup>	ISO 1183
<b>VDA Properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Fogging, G-value (condensate)	0.1 / *	mg	ISO 6452
<b>Injection</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Drying Recommended	yes	-	-
Drying Temperature	80	°C	-
Drying Time, Dehumidified Dryer	2 - 4	h	-
Processing Moisture Content	≤0.2	%	-
Melt Temperature Optimum	290	°C	-
Min. melt temperature	280	°C	-
Max. melt temperature	300	°C	-
Max. screw tangential speed	0.2 / *	m/s	-
Mold Temperature Optimum	100	°C	-
Min. mold temperature	70	°C	-
Max. mold temperature	120	°C	-
Hold pressure range	50 - 100	MPa	-
Hold pressure time	3	s/mm	-
Ejection temperature	210	°C	-

### Characteristics

Processing	• Injection Molding		
Delivery form	• Pellets		
Additives	• Lubricants	• Release agent	
Regional Availability	• North America	• Asia Pacific	• Near East/Africa
	• Europe	• South and Central America	• Global

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

#### Asia Pacific

Tel: +81 3 5521 8600

#### Europe/Middle East/Africa

Tel: +41 22 717 51 11




# DuPont™ Zytel® 77G43L NC010


## NYLON RESIN

Diagrams

Dynamic Shear modulus-temperature (dry)



Dynamic Tensile modulus-temperature (dry)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa


Tel: +41 22 717 51 11



# DuPont™ Zytel® 77G43L NC010

## NYLON RESIN

Dynamic Tensile modulus-temperature (cond.)



Revised: 2017-02-06

Page: 4 of 11

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

### Asia Pacific

Tel: +81 3 5521 8600

### Europe/Middle East/Africa

Tel: +41 22 717 51 11


Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.



# DuPont™ Zytel® 77G43L NC010

## NYLON RESIN

Stress-strain (dry)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

### Asia Pacific

Tel: +81 3 5521 8600

### Europe/Middle East/Africa


Tel: +41 22 717 51 11



# DuPont™ Zytel® 77G43L NC010

## NYLON RESIN

Stress-strain (cond.)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

### Asia Pacific

Tel: +81 3 5521 8600

### Europe/Middle East/Africa


Tel: +41 22 717 51 11



# DuPont™ Zytel® 77G43L NC010

## NYLON RESIN

Secant modulus-strain (dry)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

**North America**

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

**Asia Pacific**

Tel: +81 3 5521 8600

**Europe/Middle East/Africa**


Tel: +41 22 717 51 11



# DuPont™ Zytel® 77G43L NC010

## NYLON RESIN

Secant modulus-strain (cond.)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

**North America**

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

**Asia Pacific**

Tel: +81 3 5521 8600

**Europe/Middle East/Africa**

Tel: +41 22 717 51 11






# DuPont™ Zytel® 77G43L NC010

## NYLON RESIN

Stress-strain (isochronous) 23°C (cond.)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

### Asia Pacific

Tel: +81 3 5521 8600

### Europe/Middle East/Africa


Tel: +41 22 717 51 11




# DuPont™ Zytel® 77G43L NC010

## NYLON RESIN

Creep modulus-time 23 °C (cond.)



Tensile modulus-temperature (dry)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

**North America**

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

**Asia Pacific**

Tel: +81 3 5521 8600

**Europe/Middle East/Africa**


Tel: +41 22 717 51 11



# DuPont™ Zytel® 77G43L NC010

## NYLON RESIN

Tensile modulus-temperature (cond.)



Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 160 mil (Hytrel® measured at 80 mil), IEC Electrical properties measured at 80 mil, all ASTM properties measured at 120 mil, and test temperatures are 73°F unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

#### Asia Pacific

Tel: +81 3 5521 8600

#### Europe/Middle East/Africa

Tel: +41 22 717 51 11

