

# **Grilamid LBV-30H FWA nat** PA12-GF30

# EMS-GRIVORY | a unit of EMS-CHEMIE AG

## **Product Texts**

Product designation according to ISO 1874:

PA12, MH, 18-060, GF30

| Mechanical properties                  | dry / cond  | Unit  | Test Standard |
|--|-------------|-------|---------------|
| Tensile Modulus                        | 8000 / 7500 | MPa   | ISO 527-1/-2  |
| Stress at break                        | 130 / 120   | MPa   | ISO 527-1/-2  |
| Strain at break                        | 6/6         | %     | ISO 527-1/-2  |
| Charpy impact strength (+23°C)         | 100 / 90    | kJ/m² | ISO 179/1eU   |
| Charpy impact strength (-30°C)         | 100 / 90    | kJ/m² | ISO 179/1eU   |
| Charpy notched impact strength (+23°C) | 15 / 15     | kJ/m² | ISO 179/1eA   |
| Charpy notched impact strength (-30°C) | 10 / 10     | kJ/m² | ISO 179/1eA   |

| Mechanical properties (TPE) | dry / cond | Unit | Test Standard |
|-----------------------------|------------|------|---------------|
| Shore D hardness (15s)      | - / 83     | -    | ISO 868       |
| Ball indentation hardness   | - / 155    | MPa  | ISO 2039-1    |

| Thermal properties                           | dry / cond | Unit  | Test Standard   |
|--|------------|-------|-----------------|
| Melting temperature (10°C/min)               | 178 / -    | °C    | ISO 11357-1/-3  |
| Temp. of deflection under load (1.80 MPa)    | 155 / -    | °C    | ISO 75-1/-2     |
| Temp. of deflection under load (8.00 MPa)    | 90 / -     | °C    | ISO 75-1/-2     |
| Coeff. of linear therm. expansion (parallel) | 20 / -     | E-6/K | ISO 11359-1/-2  |
| Coeff. of linear therm. expansion (normal)   | 100 / -    | E-6/K | ISO 11359-1/-2  |
| Burning Behav. at thickness h                | HB / -     | class | IEC 60695-11-10 |
| Thickness tested                             | 0.8 / -    | mm    | IEC 60695-11-10 |
| Max. usage temperature (long term)           | 90 - 120   | °C    | ISO 2578        |
| Max. usage temperature (short term)          | 150        | °C    | EMS             |

| Electrical properties      | dry / cond | Unit  | Test Standard |
|----------------------------|------------|-------|---------------|
| Volume resistivity         | - / 1E10   | Ohm*m | IEC 60093     |
| Surface resistivity        | - / 1E11   | Ohm   | IEC 60093     |
| Electric strength          | - / 45     | kV/mm | IEC 60243-1   |
| Comparative tracking index | - / 600    | -     | IEC 60112     |

| Other properties    | dry / cond | Unit  | Test Standard  |
|---------------------|------------|-------|----------------|
| Water absorption    | 1.1 / -    | %     | Sim. to ISO 62 |
| Humidity absorption | 0.6 / -    | %     | Sim. to ISO 62 |
| Density             | 1220 / -   | kg/m³ | ISO 1183       |

| Rheo/Phys properties         | dry / cond | Unit | Test Standard   |
|------------------------------|------------|------|-----------------|
| Molding shrinkage (parallel) | 0.1 / -    | %    | ISO 294-4, 2577 |
| Molding shrinkage (normal)   | 0.5 / -    | %    | ISO 294-4, 2577 |

### Characteristics

Processing Product Attributes

Injection Molding Hydrolysis resistant

Delivery form Industry & Consumer goods

Granules Heating systems, Sanitary, water and gas supply

Created: 2017-08-11 Source: www.materialdatacenter.com

Page: 1/2

# **Grilamid LBV-30H FWA nat** PA12-GF30

## EMS-GRIVORY | a unit of EMS-CHEMIE AG

### Special Characteristics

High impact or impact modified, Improved UV resistance (outdoor use), Improved heat resistance

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

## Food Contact

EU Requirements, FDA

## Potable Water Contact

NSF 61, KTW, WRAS, ACS, DVGW W270