

# Ultradur<sup>®</sup> S 4090 G4

## PBT (Polybutylene Terephthalate)



### Product Description

Ultradur S 4090 G4 is a 20% glass reinforced PBT+ASA blend. It produces moldings with good surface finish, is resistant to chemicals and stress cracking, and has low shrinkage and warpage.

### Applications

Applications include highly stressed equipment housings in the automotive, electrical and household sectors.

PHYSICAL	ISO Test Method	Property Value
Density, g/cm <sup>3</sup>	1183	1.39
Viscosity Number, cm <sup>3</sup> /g	1628	105
Mold Shrinkage, parallel, %	294-4	0.43
Mold Shrinkage, normal, %	294-4	0.74
Moisture, %	62	
(50% RH)		0.2
(Saturation)		0.4

MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23C		6,900
Tensile stress at break, MPa	527	
-40C		160
23C		100
80C		68
120C		42
150C		32.2
Tensile strain at break, %	527	
-40C		2.7
23C		2.5
80C		4.2
120C		7.4
150C		6.7
Flexural Modulus, MPa	178	
23C		6,400
Tensile Creep Modulus (1000h), MPa	899	4,700
Tensile Creep Modulus (1h), MPa	899	5,300

IMPACT	ISO Test Method	Property Value
Izod Notched Impact, kJ/m <sup>2</sup>	180	
23C		7
Charpy Notched, kJ/m <sup>2</sup>	179	
23C		7
Charpy Unnotched, kJ/m <sup>2</sup>	179	
-30C		43
23C		55

THERMAL	ISO Test Method	Property Value
Melting Point, C	3146	223
HDT A, C	75	160
HDT B, C	75	205
Coef. of Linear Thermal Expansion, Parallel, mm/mm C		.4 X10 <sup>-4</sup>

ELECTRICAL	ISO Test Method	Property Value
Comparative Tracking Index	IEC 60112	450
Volume Resistivity (Ohm-m)	IEC 60093	>1E13
Surface Resistivity (Ohm)	IEC 60093	1E14
Dielectric Constant (100 Hz)	IEC 60250	3.7
Dielectric Constant (1 MHz)	IEC 60250	3.6
Dissipation Factor (100 Hz), E-4	IEC 60250	30
Dissipation Factor (1 MHz), E-4	IEC 60250	190

UL RATINGS	UL Test Method	Property Value
Flammability Rating, 0.71mm	UL94	HB
Relative Temperature Index, 0.71mm	UL746B	
Mechanical w/o Impact, C		130
Mechanical w/ Impact, C		90
Electrical, C		130
Flammability Rating, 1.5mm	UL94	HB
Relative Temperature Index, 1.5mm	UL746B	
Mechanical w/o Impact, C		130
Mechanical w/ Impact, C		90
Electrical, C		130
Flammability Rating, 3.0mm	UL94	HB
Relative Temperature Index, 3.0mm	UL746B	
Mechanical w/o Impact, C		130
Mechanical w/ Impact, C		90
Electrical, C		130

### Processing Guidelines

#### Material Handling

Max. Water content: 0.04%

To ensure optimum part performance, this product must be dried prior to molding and maintained at a moisture level of less than 0.04%. Dehumidifying or desiccant dryers operating at 100-120C (212-248F) for 4 hours drying time are recommended. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet. Alternatively, please contact your BASF representative.

#### Typical Profile

Melt Temperature 250-270C (482-518F)

Mold Temperature 60-100C (140-212F)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

#### Mold Temperatures

This product can be processed over mold temperatures of 60-100C (140-212F); however, for optimizing surface appearance, dimensional stability and part performance, mold surface temperatures of at least 80C (176F) are preferred.

#### Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. A maximum of 10 bar (145 psi) is recommended due to the risk of excessive shear.

#### **Fill Rate**

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

#### **Note**

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.