

Grivory XE 4217 black 9233 PA6T/66-GF45

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Product Texts

Product designation according to ISO 1874: PA6T/66+X, MH, 14-110, GF45

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	15000 / 13000	MPa	ISO 527-1/-2
Stress at break	230 / 165	MPa	ISO 527-1/-2
Strain at break	2.7 / 2.7	%	ISO 527-1/-2
Charpy impact strength (+23°C)	70 / 80	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	60 / 60	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	11 / 11	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	9/9	kJ/m²	ISO 179/1eA
Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	270 / 250	MPa	ISO 2039-1
Dan machanen maranece	2.07200	ivii u	100 2000 1
Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	300 / -	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	240 / -	°C	ISO 75-1/-2
Temp. of deflection under load (8.00 MPa)	170 / -	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	20 / -	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	70 / -	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	HB / -	class	IEC 60695-11-10
Thickness tested	0.8 / -	mm	IEC 60695-11-10
Max. usage temperature (long term)	150	°C	ISO 2578
Max. usage temperature (short term)	270	°C	EMS
Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	1E10 / 1E10	Ohm*m	IEC 60093
Surface resistivity	- / 1E12	Ohm	IEC 60093
Electric strength	45 / 45	kV/mm	IEC 60243-1
Comparative tracking index	- / 600	-	IEC 60112
Other properties	dry / cond	Unit	Test Standard
Water absorption	4.3 / -	%	Sim. to ISO 62
Humidity absorption	1.7 / -	%	Sim. to ISO 62
Density	1580 / -	kg/m³	ISO 1183
Bonony	10001	Ng/111	.55 1166
P1 /P1 /	. , , , , , , , , , , , , , , , , , , ,		T 404 1 1
Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	0.1 / -	%	ISO 294-4, 2577
Molding shrinkage (normal)	0.8 / -	%	ISO 294-4, 2577

Characteristics

Processing	Product Attributes	
Injection Molding	Improved alcohol resistance, Co Polyamide, Partially aromatic Polyamide	
Delivery form		
Granules	Automotive	
	Air intake sytems, Hydraulic systems, Fuel systems, Powertrain and Chassis , Interior	

Created: 2017-08-11 Source: www.materialdatacenter.com

Page: 1/2

The values are intended to serve as an aid in preselecting materials and for an overview of the EMS-GRIVORY product range. The information contained in this publication is based on our present knowledge and experience. The given figures and data are guidance values and do not represent binding material specifications. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are given regarding products, design, data and information. The customer is not released from his obligation to investigate the products fitness and the suitability for the intended application, compliance with legal requirements and intellectual property rights. We reserve the right to change the information at any time and without prior notice. The information in this publication is not to be considered a contractual obligation and anyliability whatsoever is expressly declined. For further questions about our products please contact our experts.

Grivory XE 4217 black 9233 PA6T/66-GF45

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Special Characteristics

Improved heat resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Electricals & Electronics

Electrical equipment

Industry & Consumer goods

Hydraulics & Pneumatics, Mechanical Engineering, Power transmission, Tools & Accessories

Created: 2017-08-11 Source: www.materialdatacenter.com